

Component Metallizations

6926



Platinum Conductor

Description:

6926 is an unfritted platinum paste, which fires to a pure platinum metal surface. 6926 has a rheology suitable for brushing.

● Key Benefits:

- Fritless paste
- Pb Free
- Pure Pt fired surface
- Can be used on alumina, zirconia or titania bodies

● Typical Properties:

Metal Type:

67.2% Platinum

Color:

Dark gray/black paste

Viscosity:

5500 – 8250 cps, Brookfield RVT, SC4-14 spindle and 6R utility cup @ 50 rpm, 25°C

FOG:

< 12 microns (at 4th streak)

● Recommended Processing Guidelines:

Printing:

280 mesh stainless steel screen.
0.5 mil emulsion

Thicknesses:

Wet: 21 - 25 microns
Dried: 11 - 15 microns
Fired: 5 - 9 microns

Coverage:

195 cm²/gram

Drying:

125°C peak temperature
15 minutes at peak temperature

Firing:

850 - 1100 °C peak temperature
Dwell time of 9-11 minutes

Thinner:

RV-372 (Terpineol)

Warranty:

Material guaranteed to meet specifications for 3 months from date of shipment.

Storage:

Store in a dry location at 5°C-25°C.
DO NOT REFRIGERATE.
Allow paste to come to room temperature prior to opening.
Spatulate well before using.

YY1010.5

Component Metallization

6926



Platinum Conductor

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Americas

Heraeus Materials Technology LLC
Thick Film Materials Division
24 Union Hill Road
West Conshohocken, PA 19428
USA
Phone: +1 (610) 825-6050
E-Mail: techservice.hcd@heraeus.com
Internet: www.thickfilm.net

Europe

W.C. Heraeus GmbH
Thick Film Materials Division
Heraeusstr. 12-14
63450 Hanau
Germany
Phone: +49 (6181) 35-5466
E-mail: th-info@heraeus.com
Internet: www.heraeus-thickfilm.com

Asia

Heraeus Materials Technology
Shanghai Ltd.
No. 1 Guang Zhong Road
Zhuangqiao Town, Minhang District
Shanghai 201108
People's Republic of China
Phone: + 86 (21) 3357-5688
E-Mail: th.hmts@heraeus.com
Internet: www.heraeus-thickfilm.com