

Component Metallizations

CL11-7840

Platinum Conductor

Description:

CL11-7840 is a platinum conductor designed to be used in conjunction with a high fire, high alumina ceramic body. CL11-7840 is used in critical applications where corrosion resistance is essential. It can be used to fill large cavities or as an inner conductor.

● Key Benefits:

- Cofireable
- Pure Platinum
- Inert ceramic filler is added to reduce shrinkage
- Corrosion Resistant

● Typical Properties:**Viscosity:**

250-350 Kcps Brookfield HBT.
SC4-14 spindle and a 6 R utility cup
@ 10rpm, 25°C.

Solids:

83.0 ± 1%

● Recommended Processing Guidelines:**Printing:**

250-325 mesh screen
0.5 mil emulsion.
Can also be stencil printed.

Drying:

100-150°C for 10 minutes

Firing:

1000-1400°C peak firing temperature

Thinner:

Heraeus RV-372 (Terpineol)

Warranty:

Material guaranteed to meet specifications
for 6 months from date of shipment.

Storage:

Store in a dry location at 5°C-25°C.
DO NOT REFRIGERATE.
Allow paste to come to room temperature prior to opening.
Spatulate well before using.

Component Metallizations

CL11-7840

Platinum Conductor

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Europe
W.C. Heraeus GmbH & Co. KG
Circuit Materials Division
Heraeusstr. 12-14
63450 Hanau/Germany
Tel: +49 (6181) 35-5466
E-Mail: cmdinfo@heraeus.com
Internet: www.4cmd.com

North America
Heraeus Incorporated
Circuit Materials Division
24 Union Hill Road
W. Conshohocken, PA 19428
USA
Tel: +1 (610) 825-6050
E-Mail: techservice@4cmd.com

Asia
Heraeus Ltd
Heraeus Technology Centre
30 On Chuen Street
On Lok Tsuen
Fanling, NT., Hong Kong
Tel: + (852) 2675-1200
E-Mail: pdf@heraeus.com.hk