

■ ■ ■ ■ **Component Metallizations** ■ ■ ■ ■

**CL11-8822**

**PT VIA FILL CONDUCTOR**

**Description:**

CL11-8822 is a pure Pt paste designed to be used in as a via fill paste in high fire applications where corrosion resistance is essential.

● **Key Benefits**

- Cofireable
- Via fill applications
- Corrosion Resistant

● **Typical Properties:**

**Viscosity:**

175-225 Kcps Brookfield, HBT,  
Paar Physica, 10 sec<sup>-1</sup>, 25°C

**Solids:**

83.0%±1

● **Recommended Processing Guidelines:**

**Printing:**

280-325 mesh stainless steel screen  
0.5 mil emulsion

**Drying:**

Dry at 100-150°C for 10 minutes

**Firing:**

1000-1400°C peak temperature

**Thinner:**

RV-507 (Texanol)

**Warranty:**

Material guaranteed to meet specifications for 6 months from date of shipment.

**Storage:**

Store in a dry location at 5°C-25°C.

**DO NOT REFRIGERATE**

Allow paste to come to room temperature prior to opening.

Spatulate well before using.

YY0307.1

### Component Metallizations

### CL11-8822

PT VIA FILL CONDUCTOR

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

#### Americas

Heraeus Incorporated  
Thick Film Materials Division  
24 Union Hill Road  
West Conshohocken, PA 19428  
USA  
Phone: +1 (610) 825-6050  
E-Mail: [techservice.hcd@heraeus.com](mailto:techservice.hcd@heraeus.com)  
Internet: [www.thickfilm.net](http://www.thickfilm.net)

#### Europe

W.C. Heraeus GmbH  
Thick Film Materials Division  
Heraeusstr. 12-14  
63450 Hanau  
Germany  
Phone: +49 (6181) 35-5466  
E-mail: [th-info@heraeus.com](mailto:th-info@heraeus.com)  
Internet: [www.heraeus-th.com](http://www.heraeus-th.com)

#### Asia

Heraeus Materials Technology  
Shanghai Ltd.  
No. 1 Guang Zhong Road  
Zhuangqiao Town, Minhang District  
Shanghai 201108  
People's Republic of China  
Phone: + 86 (21) 6442-6838  
E-Mail: [th.hmts@heraeus.com](mailto:th.hmts@heraeus.com)  
Internet: [www.heraeus-th.com](http://www.heraeus-th.com)