

Capacitor Materials

ET1890A



Lead Free Plateable Silver End Termination

Description:

ET1890A is a Pb and Cd free nickel plateable silver end termination designed to be compatible on Multilayer ceramic chip capacitors (NPO and X7R bodies). Nickel plating can be done without pre-plate processing due to the low glass content on the fired surface.

The rheology of ET1890A is suitable for machine dipping.

● Key Benefits:

- Lead and Cadmium free
- Nickel plateable-no pre-plate processing
- Low usage-excellent coverage uniformity
- Excellent Hermeticity

● Typical Properties:

Metal type:

Silver

Viscosity:

40-50 Kcps; Brookfield RVT,
SC4-14 spindle and 6R utility cup
@ 10 rpm, 25°C.

Solids:

76.5 ± 1.5%

F.O.G.:

≤10 microns (4th scratch)

● Recommended Processing Guidelines:

Drying:

>150°C for 8 minutes
Peak temperature of 175°C for 2 minutes
20 minute total cycle time

Firing profile:

Peak Temp: 650°C - 800°C
Ramp rate (ambient-peak temp) : 120°C/min.
Dwell time at temp 5-7 minutes

Thinner:

RV-372 (Terpineol)

Warranty:

Material guaranteed to meet specifications
for 6 months from date of shipment.

Storage :

Store in a dry location at 5°C-25°C.

DO NOT REFRIGERATE.

Allow paste to come to room temperature
prior to opening.

Spatulate well before using.

YY1010.4

Capacitor Materials

ET1890A



Lead Free Plateable Silver End Termination

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Americas

Heraeus Materials Technology LLC
Thick Film Materials Division
24 Union Hill Road
West Conshohocken, PA 19428
USA
Phone: +1 (610) 825-6050
E-Mail: techservice.hcd@heraeus.com
Internet: www.thickfilm.net

Europe

W.C. Heraeus GmbH
Thick Film Materials Division
Heraeusstr. 12-14
63450 Hanau
Germany
Phone: +49 (6181) 35-5466
E-mail: th-info@heraeus.com
Internet: www.heraeus-thickfilm.com

Asia

Heraeus Materials Technology
Shanghai Ltd.
No. 1 Guang Zhong Road
Zhuanqiao Town, Minhang District
Shanghai 201108
People's Republic of China
Phone: + 86 (21) 3357-5688
E-Mail: th.hmts@heraeus.com
Internet: www.heraeus-thickfilm.com