

Conductors

C4729



Silver/Platinum Conductor

Description:

C4729 is a lead, nickel and cadmium free Ag/Pt conductor, designed for automotive applications. C4729 is a new member of Heraeus' line of lead free conductors with excellent fired film density, high conductivity, good solder leach resistance, excellent aged adhesion and aluminum wire bondable.

● Key Benefits

- Lead, nickel and cadmium free
- Excellent aged adhesion
- Dense fired film
- Good Al wire bond adhesion (initial and aged)

● Typical Properties:

Resistivity:

≤ 5 milliohms per square
at 12 microns fired film thickness.

Viscosity

120 -180 Kcps
Brookfield HBT SC4-14 spindle
and 6R utility cup @ 10 rpm, 25°C

Solderability:

80 x 80 mil pad
62Sn/36Pb/2Ag @ 230°C ± 5°C
5 ± 1 sec. dip
RMA flux
≥ 95% solder coverage

Solder Leaching:

** (10 sec dips)

	#of Dips**	% Line Loss
Sn62/Pb36/Ag2	1	≤ 10%
230°C, RMA flux	3	≤ 15%

Adhesion:

80 x 80 mil pad
62Sn/36Pb/2Ag @ 230°C ± 5°C
Forced air box oven
Initial: ≥ 5 lbs
1,000 hours @ 150°C: ≥ 4 lbs

% Solids:

79.5 ± 1%

Wire Bond Adhesion:

10 mil Al wire
99.999% Al, Elongation > 5%
5 x 850°C firing
Initial > 500 gms
1,000 hours @ 150°C > 450 gms

● Recommended Processing Guidelines:

Printing:

230 - 325 mesh stainless steel screen.
0.5 mil emulsion

Drying:

Dry at 150°C for 10 minutes.

Firing:

850°C peak temperature
Dwell time of 10-12 minutes.
Total cycle time of 36 – 60 minutes

Film Thickness:

Wet: 34-42 microns
Dried: 23 - 27 microns
Fired: 10 -14 microns

Thinner:

RV-372 (Terpineol)

Warranty:

Material guaranteed to meet specifications
for 6 months from date of shipment.

Storage:

Store in a dry location at 5°C-25°C.
DO NOT REFRIGERATE.
Allow paste to come to room temperature
prior to opening.
Spatulate well before using.

YY1010.11

Conductors

C4729



Silver/Platinum Conductor

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Americas
Heraeus Materials Technology LLC
Thick Film Materials Division
24 Union Hill Road
West Conshohocken, PA 19428
USA
Phone: +1 (610) 825-6050
E-Mail: techservice.hcd@heraeus.com
Internet: www.thickfilm.net

Europe
W.C. Heraeus GmbH
Thick Film Materials Division
Heraeusstr. 12-14
63450 Hanau
Germany
Phone: +49 (6181) 35-5466
E-mail: th-info@heraeus.com
Internet: www.heraeus-thickfilm.com

Asia
Heraeus Materials Technology
Shanghai Ltd.
No. 1 Guang Zhong Road
Zhuanqiao Town, Minhang District
Shanghai 201108
People's Republic of China
Phone: + 86 (21) 3357-5688
E-Mail: th.hmts@heraeus.com
Internet: www.heraeus-thickfilm.com