

## Conductors

### C5799

#### Gold Via Fill

**Description:**

C5799 is a screen printable gold via fill conductor designed for use in multilayer hybrids. It is designed to be used with either IP9117 or IP9118. It gives excellent surface coplanarity along with good electrical conductivity.

● **Key Benefits:**

- Outstanding via fill to dielectric adhesion
- Excellent surface coplanarity
- Good conductivity
- Easy to process
- Ideal interface for Au bearing conductors

● **Typical Properties:**

**Resistivity:**

≤ 15.0 milliohms per square  
at 25 microns fired film thickness

**Coverage:**

68 cm<sup>2</sup>/g

**Viscosity:**

250-400 Kcps Brookfield HBT SC4-14 spindle  
and 6R utility cup @ 10 rpm, 25°C

**Solids:**

86.0 ± 1%

● **Recommended Processing Guidelines:**

**Processing Sequence:**

- Print/Dry/Fire Bottom Conductor
- Print/Dry/Fire 1st Dielectric
- Print/Dry/Fire 2nd Dielectric
- Print/Dry/Fire C5799
- Print/Dry/Fire 3rd Dielectric
- Option A:  
Print/Dry/Fire conductor as via fill  
Print/Dry/Fire next conductor layer
- Option B:  
Print/Dry/Fire next conductor layer
- Option C:  
Print/Dry/Fire C5799  
Print/Dry/Fire Conductor layer

**Printing:**

325 mesh Stainless steel screen  
0.8 mil emulsion

**Thickness:**

Fired: 20-26 microns

**Drying:**

Dry at 150°C for 10 minutes.

**Firing:**

875°C peak  
Dwell time of 8-12 minutes.

**Compatibility:**

Conductors: C5789, C5790  
Dielectric: IP9118, IP9117W, IP9117

**Thinner:**

Heraeus RV-372 (Terpineol)

**Warranty:**

Material guaranteed to meet specifications  
for 6 months from date of shipment.

**Storage:**

Store in a dry location at 5°C -25°C.  
DO NOT REFRIGERATE.  
Allow paste to come to room temperature  
prior to opening.  
Spatulate well before using.

## Conductors

### C5799

#### Gold Via Fill

---

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

#### Americas

Heraeus Incorporated  
Thick Film Materials Division  
24 Union Hill Road  
West Conshohocken, PA 19428  
USA  
Phone: +1 (610) 825-6050  
E-Mail: [techservice.hcd@heraeus.com](mailto:techservice.hcd@heraeus.com)  
Internet: [www.thickfilm.net](http://www.thickfilm.net)

#### Europe

W.C. Heraeus GmbH  
Thick Film Materials Division  
Heraeusstr. 12-14  
63450 Hanau  
Germany  
Phone: +49 (6181) 35-5466  
E-mail: [th-info@heraeus.com](mailto:th-info@heraeus.com)  
Internet: [www.heraeus-th.com](http://www.heraeus-th.com)

#### Asia

Heraeus Materials Technology  
Shanghai Ltd  
No. 1 Guang Zhong Road  
Zhuangqiao Town, Minhang District  
Shanghai 201108  
People's Republic of China  
Phone: + 86 (21) 6442-6838  
E-Mail: [th.hmts@heraeus.com](mailto:th.hmts@heraeus.com)  
Internet: [www.heraeus-th.com](http://www.heraeus-th.com)