

Conductors

C7257

Nitrogen Fireable Copper Conductor

Description:

C7257 copper conductor is a practical alternative to precious metal materials in many applications. The advanced powder technology in C7257 results in improved fired film properties.

● **Key Benefits :**

- Exceptionally high conductivity
- Migration resistant
- Low cost
- Leach resistant

● **Typical Properties:**

Resistivity :

≤ 2.6 milliohms per square
at 13 microns fired film thickness

Adhesion :

80x80 mil pad
62Sn/36Pb/2Ag @ 230°C
RMA flux
Initial ≥ 5.0 lbs
Aged ≥ 3.0 lbs (48 hours @ 150°C)

Solderability :

63Sn/37Pb @ 230°C
5 sec dip, RMA flux
>95%

Solder Leaching :

	<u>10 sec Dips</u>	<u>% Line Lost</u>
63Sn/37Pb @ 230°C	3	≤ 5%
RMA Flux	6	≤ 10%

Coverage:

100 cm²/g

Viscosity :

135-165 Kcps, Brookfield HBT,
SC4-14@ 10 rpm, 25°C.

Solids:

90.0 ±1%

● **Recommended Processing Guidelines:**

Printing :

280 stainless steel mesh screen
0.5 mil emulsion

Drying :

Dry at 125°C for 15 minutes.

Firing Profile :

Fire in Nitrogen
900°C peak
Dwell time of 9-11 minutes.
Typical rise time of 20-23 minutes
(measured from 100°C entry point)
Total cycle time of 50-65 minutes

Line Resolution:

8 mils (200 microns)

Thickness :

Dried: 28 microns
Fired: 11-15 microns

Thinner :

Heraeus RV-507 (Texanol®)

Warranty:

Material guaranteed to meet specifications for 6 months from date of shipment.

Storage :

Store in a dry location at 5°C-25°C.

DO NOT REFRIGERATE.

Allow paste to come to room temperature prior to opening.
Spatulate well before using.

YY1010.8

Conductors

C7257

Nitrogen Fireable Copper Conductor

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Americas

Heraeus Materials Technology LLC
Thick Film Materials Division
24 Union Hill Road
West Conshohocken, PA 19428
USA
Phone: +1 (610) 825-6050
E-Mail: techservice.hcd@heraeus.com
Internet: www.thickfilm.net

Europe

W.C. Heraeus GmbH
Thick Film Materials Division
Heraeusstr. 12-14
63450 Hanau
Germany
Phone: +49 (6181) 35-5466
E-mail: th-info@heraeus.com
Internet: www.heraeus-thickfilm.com

Asia

Heraeus Materials Technology
Shanghai Ltd.
No. 1 Guang Zhong Road
Zhuanqiao Town, Minhang District
Shanghai 201108
People's Republic of China
Phone: + 86 (21) 3357-5688
E-Mail: th.hmts@heraeus.com
Internet: www.heraeus-thickfilm.com