

## Conductors

### C 1075 S (LPA 409-021)

#### REACH Compliant Silver Conductor Paste

##### Description

C 1075 S (LPA 409-021) is a low cost, oxide-bond pure Ag conductor material. They offer cost savings over standard Ag/Pd formulations, while maintaining the advantages of leach resistance and aged adhesion. C 1075 S (LPA 409-021) is for use on alumina. Resulting films are dense and uniform.

##### Key Benefits

- Excellent solderability and leach resistance on alumina
- Compatible with HERAEUS resistors
- Good initial and aged adhesion
- Outstanding conductivity
- Free of cadmium and nickel
- REACH<sup>3</sup> and RoHS<sup>4</sup> compliant

##### Processing

1. Spatulate well prior to processing. When stored in a fridge: The paste should have acquired room temperature before being opened, to avoid condensation.
2. Print through a 200 - 325 mesh stainless steel screen. Total thickness: 50 - 110 µm
3. Level at room temperature for 5 - 10 minutes.
4. Dry at 150°C for 10 - 20 minutes.
5. Fire at 850°C (peak) for 10 minutes, and with a total firing cycle time of c. 30 - 60 minutes.

Thinner

HVS 100

##### Typical Properties (Pastes)

Form:	Thixotropic paste
Viscosity:	30 - 50 Pas (25°C, D = 100 s <sup>-1</sup> )
Solids:	81.5 % ± 1.0 %
Printing Speed:	Up to 20 cm / s
Coverage:	c. 80 cm <sup>2</sup> / g (FFT: 12 µm)
Shelf Life:	6 months from date of shipment with correct storage (in a dry, cool (2 to 23 °C) and dark place with container tightly shut).

##### Typical Properties (Fired)<sup>1</sup>

Fired Film Thickness <sup>2</sup> : (FFT)	13.0 – 16.0 µm
Resistivity <sup>2</sup> :	≤ 2.2 mΩ/□ (FFT: 12 µm)
Solderability: (62Sn / 36Pb / 2Ag)	Good ≥ 95% (235°C, 5s dip) (assessment acc. DIN 41850-2E)
Adhesion, Aged: (62Sn / 36Pb / 2Ag)	≥ 20 N (48 hrs, 150 °C)
Leach Resistance: (62Sn / 36Pb / 2Ag)	≥ 4 dips (235 °C, 10s each)

##### Compatibility

Dielectrics:	IP 9117 Series
Resistors:	R 8900 Series R 8900 (WP09-XY) Series

## Conductors

### C 1075 S (LPA 409-021)

#### REACH Compliant Silver Conductor Paste

- 1 Typical property based on laboratory test methods. For optimum results all materials should be fired in a profiled furnace supplied with dried, hydrocarbon and other contaminant free air (PP-1).
- 2 Measured after printing with a 200 mesh steel screen; thickness of screen and emulsion combined was c. 100 µm, and the resultant printed track was 500 µm wide.
- 3 REACH compliant according to the Commission Regulation (EU) No 143/2011 of 17 February 2011 amending Annex XIV to Regulation (EC) No 1907/2006 of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments; the above mentioned product does not contain any substance listed in the Annex XIV.
- 4 RoHS compliant according to the Directives (European Union) No 2011/65/EC of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions No. 7. c. I of the EU Directive e.g. related to Pb)

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

#### Europe [TH]

Heraeus Precious Metals GmbH & Co. KG  
Thick Film Materials Division  
Heraeusstr. 12 – 14  
63450 Hanau  
Germany  
Tel: +49 (6181) 35 - 5466  
E-Mail: [th-info@heraeus.com](mailto:th-info@heraeus.com)  
Internet: [www.heraeus-thickfilm.com](http://www.heraeus-thickfilm.com)

#### Americas [TH]

Heraeus Materials Technology LLC  
Thick Film Materials Division  
24 Union Hill Road  
W. Conshohocken, PA 19428  
USA  
Tel: +1 (610) 825 - 6050  
E-Mail: [techservice.hcd@heraeus.com](mailto:techservice.hcd@heraeus.com)  
Internet: [www.heraeus-thickfilm.com](http://www.heraeus-thickfilm.com)

#### Asia [TH]

Heraeus Materials Technology Shanghai Ltd.  
No. 1 Guang Zhong Road  
Zhuanquiao Town, Minhang District  
201108 Shanghai  
People's Republic of China  
Tel: +86 (21) 3357 - 5688  
E-Mail: [th.hmmts@heraeus.com](mailto:th.hmmts@heraeus.com)  
Internet: [www.heraeus-thickfilm.com](http://www.heraeus-thickfilm.com)