

## Conductors

### C 1076 SD

#### Silver Conductor Paste

##### Description:

C 1076 SD is a low cost Ag / Pt conductor material that utilizes a oxide bond system for providing particularly excellent adhesion to alumina and beryllium oxide substrates. The material can easily be used to print fine line patterns or large-area ground planes.

C 1076 SD is also for use in multilayer applications, in combination with dielectric IP 9xxx series. In this regard, it is particularly useful as an inner-layer conductor.

Resulting film is dense and uniform, and features all the advantages of a fritless system.

- Excellent solderability and leach resistance
- Solderable on alumina and dielectric IP 9xxx series
- Compatible with HERAEUS resistors
- Excellent initial and aged adhesion, even after multiple firings
- Inner layer for multilayer applications
- Very good conductivity
- Aluminum and gold wire bondable
- Via-fill and trough-hole "silver"
- Entirely cadmium- and nickel-free

##### Processing:

1. Spatulate well prior to processing. When stored in a fridge: The paste should have acquired room temperature before being opened, to avoid condensation.
2. Print through a 200 – 325 mesh stainless steel screen. Total thickness: 50 – 110 µm.
3. Level at room temperature for 5 – 10 minutes.
4. Dry at 150°C for 10 – 20 minutes.
5. Fire at 850°C (peak) for 10 minutes, and with a total firing cycle time of c. 30 – 60 minutes.

**Thinner:** HVS 100, RV 372

##### Properties (Pastes):

Viscosity:	30 – 50 Pas (25°C, D = 100 s <sup>-1</sup> )
Solids:	82.0 % +/- 1.5 %
Printing Speed:	up to 20 cm / s
Coverage:	c. 80 cm <sup>2</sup> / g (FFT: 12 µm)
Shelf Life:	12 months with correct storage (2 to 23°C, in a cool, dry, dark place and with the container tightly shut).

##### Properties (Fired) <sup>1</sup>:

Fired Film Thickness <sup>2</sup> :	12.5 – 15.5 µm
Line Definition:	≥ 125 µm
Resistivity <sup>2</sup> :	≤ 4.0 mΩ / □ (FFT: 12 µm)
Solderability: (62Sn / 36Pb / 2Ag)	Good = ≥ 95% (235°C, 5s dip) (assessment acc. DIN 41850-2 E)
Adhesion: (62Sn / 36Pb / 2Ag)	
Initial:	C 1076 SD ≥ 20 N
Aged: (48 hrs, 150°C)	C 1076 SD ≥ 18 N
Leach Resistance: (62Sn / 36Pb / 2Ag)	≥ 5 dips (235°C, 10s each)

##### Compatibility:

Dielectrics:	IP 9xxx series
Resistors:	R 8900 / D / E / ED series R 400 H / L series

- 1 Typical property based on laboratory test methods. For optimum results all materials should be fired in a profiled furnace supplied with dried, hydrocarbon-free and other contaminant-free air (PP-1).
- 2 Measured after printing with a 200 mesh steel screen; screen thickness and emulsion thickness combined was c. 100 µm, and the resultant printed track was 500 µm wide.

## Conductors

### C 1076 SD

#### Silver Conductor Paste

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Europe [TH]  
W.C. Heraeus GmbH  
Thick Film Materials Division  
Heraeusstr. 12 – 14  
63450 Hanau  
Germany  
Tel: +49 (6181) 35 – 5466  
E-Mail: [th-info@heraeus.com](mailto:th-info@heraeus.com)  
Internet: [www.heraeus-th.com](http://www.heraeus-th.com)

North America  
Heraeus Incorporated  
Thick Film Materials Division  
24 Union Hill Road  
W. Conshohocken, PA 19428  
USA  
Tel: +1 (610) 825 – 6050  
E-Mail: [techservice.hcd@heraeus.com](mailto:techservice.hcd@heraeus.com)  
Internet: [www.thickfilm.net](http://www.thickfilm.net)

Asia [TH]  
Heraeus Materials Technology Shanghai Ltd.  
No. 1 Guang Zhong Road  
Zhuanquiao Town, Minhang District  
201108 Shanghai  
People's Republic of China  
Tel: +86 (21) 6442 6838  
E-Mail: [th.hmts@heraeus.com](mailto:th.hmts@heraeus.com)  
Internet: [www.heraeus-th.com](http://www.heraeus-th.com)