

Conductors

C 3605 P / C 3605 S



Platinum Conductor Paste

Description

C 3605 P and C 3605 S are pastes only consisting of Pt powder and organic vehicle. They are intended to be mixed with customer specific adhesion promoters or to be co-fired with tape.

C 3605 P and C 3605 S can – depending on the exact viscosity which is delivered – be either sprayed / brushed ("P"-version) or screen printed ("S"-version).

They are particularly useful for the manufacture of O₂ sensors.

Key Benefits

- Fritless pastes
- Chemically resistant
- Can be used on alumina, zirconia or other bodies
- Free of lead, cadmium and nickel
- REACH² and RoHS³ compliant

Processing

1. Spatulate well prior to processing. When stored in a fridge: The paste should have acquired room temperature before being opened, to avoid condensation.
2. Print through a 200 – 325 mesh stainless steel screen.
3. Level at room temperature for 10 minutes.
4. Dry at 125 – 150°C for 10 – 20 minutes.
5. Fire at 1100°C – 1500°C (peak) for 5 – 30 minutes, and with a total firing cycle time of c. 30 – 60 minutes.

Thinner

HVS 100

Typical Properties (Paste)¹

Form:

"P" – version: Sprayable / brushable
 "S" – version: Screen printable

Viscosity:

"P" – version: Not measured (very low)
 "S" – version: 25 – 45 Pas
 (25°C, D = 50 s⁻¹)

Printing Speed:
 ("S" version)

Up to at least 10 cm / s

Shelf Life:

"S" – version: 6 months
 "P" – version: 3 months
 from date of shipment with correct storage (in a dry, cool (2 to 23°C) and dark place with container tightly shut)

Compatibility

Substrates:

Quartz, Al₂O₃, ZrO₂,
 Mica, Porcelain

Conductors

C 3605 P / C 3605 S



Platinum Conductor Paste

- 1 Typical property based on laboratory test methods. For optimum results all materials should be fired in a profiled furnace supplied with dried, hydrocarbon and other contaminant free air (PP-1).
- 2 REACH compliant according to the Commission Regulation (EU) No 143/2011 of 17 February 2011 amending Annex XIV to Regulation (EC) No 1907/2006 of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency and its subsequent amendments; we define a material as REACH compliant, as long as substances used are not recorded in the Annex XIV.
- 3 RoHS compliant according to the Directives (European Union) No 2011/65/EC of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions No. 7.c. 1 of the EU Directive e.g. related to Pb)

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Europe [TH]
Heraeus Precious Metals GmbH & Co. KG
Thick Film Materials Division
Heraeusstr. 12 – 14
63450 Hanau
Germany
Tel: +49 (6181) 35 - 5466
E-Mail: th-info@heraeus.com
Internet: www.heraeus-thickfilm.com

North America
Heraeus Materials Technology LLC
Thick Film Materials Division
24 Union Hill Road
W. Conshohocken, PA 19428
USA
Tel: +1 (610) 825 - 6050
E-Mail: techservice.hcd@heraeus.com
Internet: www.heraeus-thickfilm.com

Asia [TH]
Heraeus Materials Technology Shanghai Ltd.
No. 1 Guang Zhong Road
Zhuanquiao Town, Minhang District
201108 Shanghai
People's Republic of China
Tel: +86 (21) 3357 - 5688
E-Mail: th.hmts@heraeus.com
Internet: www.heraeus-thickfilm.com