

Conductors

C 3605 P / S

Platinum Conductor Paste

Description:

C 3605 P / S are pastes only consisting of Pt-powder and organic vehicle. They are intended to be mixed with customer specific adhesion promoters or to be co-fired with tape.

C 3605 P / S can – depending on the exact viscosity which is delivered – be either sprayed or brushed (“P”-version), or screen printed (“S”-version).

They are particularly useful for the manufacture of O₂ sensors.

Processing:

1. Spatulate well prior to processing. When stored in a fridge: The paste should have acquired room temperature before being opened, to avoid condensation.
2. Print through a 200 – 325 mesh stainless steel screen.
3. Level at room temperature for 10 minutes.
4. Dry at 125 – 150°C for 10 – 20 minutes.
5. Fire at 1100°C – 1500°C (peak) for 5 – 30 minutes, and with a total firing cycle time of c. 30 – 60 minutes.

Thinner: HVS 100

Properties (Paste) *:

Form:

“P” – version:

sprayable / brushable

“S” – version:

screen - printable

Viscosity:

“P” – version:

Not measured (very low)

“S” – version:

25 – 45 Pas
(25°C, D = 50 s⁻¹)

Printing Speed:

(“S” version)

Up to at least 10 cm / s

Shelf Life:

“S” – version

6 months

“P” – version

3 months
with correct storage (2 to 23°C,
in a cool, dry, dark place and
with the container tightly shut).

Substrate:

Quartz, Al₂O₃, ZrO₂,
Mica, Porcelain

* Typical property based on laboratory test methods. For optimum results all materials should be fired in a profiled furnace supplied with dried, hydrocarbon-free and other contaminant-free air (PP-1).

Conductors

C 3605 P / S

Platinum Conductor Paste

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Europe [TH]
W. C. Heraeus GmbH
Thick Film Materials Division
Heraeusstr. 12 – 14
63450 Hanau
Germany
Tel: +49 (6181) 35 – 5466
E-Mail: th-info@heraeus.com
Internet: www.heraeus-th.com

North America
Heraeus Incorporated
Thick Film Materials Division
24 Union Hill Road
W. Conshohocken, PA 19428
USA
Tel: +1 (610) 825 – 6050
E-Mail: techservice.hcd@heraeus.com
Internet: www.thickfilm.net

Asia [TH]
Heraeus Materials Technology Shanghai Ltd.
No. 1 Guang Zhong Road
Zhuanquiao Town, Minhang District
201108 Shanghai
People's Republic of China
Tel: +86 (21) 3357 - 5473
E-Mail: th.hmts@heraeus.com
Internet: www.heraeus-th.com