

Conductors

C 2230



(LPA 508-100) Silver / Palladium Conductor Paste (DPIS*)

* Development Product Information Sheet

Description:

C 2230 is a 3:1 Ag / Pd conductor paste which exhibits a high density, high reliability and good fine line resolution. The surface of the fired material is very smooth. It is both mechanically and chemically very resistant and is hence a recommended material for applications such as fuel sensors. Conductivity, leach resistance and resistance to silver migration are all good.

Properties (Pastes):

Viscosity:	30 – 50 Pas (25°C, D = 100 s ⁻¹)
Printing Speed:	Up to 20 cm / s
Shelf Life:	6 months, with correct storage (5 – 25 °C in a cool, dry, dark place, and with the jar tightly shut).

Processing:

1. Spatulate well prior to processing. When stored in a fridge: The paste should have acquired room temperature before being opened, to avoid condensation.
2. Print through a 325 mesh stainless steel screen. Total thickness: approx. 75 µm
3. Level at room temperature for 5 – 10 minutes.
4. Dry at 150°C for 10 – 20 minutes.
5. Fire at 850°C (peak) for 10 minutes, and with a total firing cycle time of c. 30 – 60 minutes.

Properties (Fired)¹:

Fired Film Thickness ² : (FFT)	8.0 – 12.0 µm
Line Definition:	≥ 125 µm
Resistivity ² :	≤ 40 mΩ / □ (FFT: 12 µm)
Aged Adhesion: (96 Sn / 3.5 Ag / 0.5 Cu; 48 hrs, 150°C)	≥ 20 N
Leach Resistance:	
96 Sn / 3.5 Ag / 0.5 Cu	≥ 2 dips (255°C, 5s each)
62 Sn / 36 Pb / 2 Ag	≥ 4 dips (235°C, 10s each)

Thinner: HVS 507

1 Typical property based on laboratory test methods. For optimum results all materials should be fired in a profiled furnace supplied with dried, hydrocarbon-free and other contaminant-free air (PP-1).

2 Measured after printing with a 325 mesh steel screen; screen thickness and emulsion thickness combined was c. 75 µm, and the resultant printed track was 500 µm wide.

Conductors

C 2230



(LPA 508-100) Silver / Palladium Conductor Paste (DPIS*)

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Europe [TH]
W.C. Heraeus GmbH
Thick Film Materials Division
Heraeusstr. 12 – 14
63450 Hanau
Germany
Tel: +49 (6181) 35-5466
E-Mail: th-info@heraeus.com
Internet: www.heraeus-thickfilm.com

North America
Heraeus Incorporated
Thick Film Materials Division
24 Union Hill Road
W. Conshohocken, PA 19428
USA
Tel: +1 (610) 825-6050
E-Mail: techservice.hcd@heraeus.com
Internet: www.heraeus-thickfilm.com

Asia [TH]
Heraeus Materials Technology Shanghai Ltd.
No. 1 Guang Zhong Road
Zhuanquiao Town, Minhang District
201108 Shanghai
People's Republic of China
Tel: +86 (21) 3357-5473
E-Mail: th.hmts@heraeus.com
Internet: www.heraeus-thickfilm.com