

Polymers

PD5200 White

Epoxy Insulator

Description:

PD5200 White is a, screen printable, single component and fast curing modified epoxy coating used for circuit protection and identification. This white cover coat, when properly cured, yields a chemically inert film which will not react with circuit components. PD5200 White provides excellent adhesion to a variety of substrate materials.

● **Key Benefits:**

- RoHS compliant*
- REACH compliant**
- Screen printable
- Fast curing
- Yields a chemically inert film which will not react with circuit components

● **Typical Properties:**

Dielectric Breakdown Voltage:

> 1000 volts/mil

Non-Volatile

96% ± 2%

Viscosity:

70-140 Kcps, Brookfield HBT,
SC4-14 spindle and 6R cup @ 10 rpm, 25°C

Insulation Resistance:

> 1x10¹⁰ ohms

Dielectric Constant:

> 12

● **Recommended Processing Guidelines:**

Printing:

280-325 mesh stainless steel screen
0.5 mil emulsion

Curing:

30 – 60 minutes @ 150°C

Cured Thickness:

40-50 microns per layer with 2 layers recommended

Coverage:

127 cm²/g @ 40 microns
Wet film thickness

Thinner:

RV-221

Warranty:

Material guaranteed to meet specifications for
6 months from date of shipment.

Storage:

Refrigerate 5°C-10°C to ensure proper performance of
shelf life.
Allow paste to come to room temperature prior to opening.
Spatulate well before using

Handling & Precautions:

Use in a well ventilated area.
In general, avoid contact with skin.
Wash with soap and water.

For cleanup of uncured epoxy material, a one-to-one
mixture of Methyl Ethyl Ketone (MEK) and Toluene is
recommended.

YY0911.5

***RoHS Statement**

Compliant according to Directives (European Union) No 2011/65/EC of Restriction of Hazardous Substances ("RoHS") and its subsequent amendments (including the exceptions No. 5 and 7 of the EU Directive e.g. related to Pb bounded in a glass matrix as oxide PbO)

****REACH Statement**

Compliant according to the Commission Regulation (EU) No 143/2011 of Feb. 17, 2011 amending Annex XIV to Regulation (EC) No 1907/2006 of the European Parliament and of the council on the Registration, Evaluation, Authorisation and Restriction of Chemicals ("REACH") by European Chemicals Agency.

Polymers

PD5200 White

Epoxy Insulator

The descriptions and engineering data shown here have been compiled by Heraeus using commonly-accepted procedures, in conjunction with modern testing equipment, and have been compiled as according to the latest factual knowledge in our possession. The information was up-to date on the date this document was printed (latest versions can always be supplied upon request). Although the data is considered accurate, we cannot guarantee accuracy, the results obtained from its use, or any patent infringement resulting from its use (unless this is contractually and explicitly agreed in writing, in advance). The data is supplied on the condition that the user shall conduct tests to determine materials suitability for a particular application.

Americas

Heraeus Materials Technology LLC
Thick Film Materials Division
24 Union Hill Road
West Conshohocken, PA 19428
USA
Phone: +1 (610) 825-6050
E-Mail: techservice.hcd@heraeus.com
Internet: www.thickfilm.net

Europe

Heraeus Precious Metals GmbH & Co. KG
Thick Film Materials Division
Heraeusstr. 12-14
63450 Hanau
Germany
Phone: +49 (6181) 35-5466
E-mail: th-info@heraeus.com
Internet: www.heraeus-thickfilm.com

Asia

Heraeus Materials Technology
Shanghai Ltd.
No. 1 Guang Zhong Road
Zhuanqiao Town, Minhang District
Shanghai 201108
People's Republic of China
Phone: + 86 (21) 3357-5688
E-Mail: th.hmmts@heraeus.com
Internet: www.heraeus-thickfilm.com